




# Monofile Tressengewebe

Artikel	 Luftdurchlass bei 20 mm WS l/m <sup>2</sup> /s	 Gewicht in g/m <sup>2</sup>	 Dicke in μm
PVDF-350/500	350	500	440
PA12-1025/310	1025	310	630
PP-90/290	90	290	390
PP-95/210	95	210	320
PP-100/136	100	136	200
PP-190/235	190	235	380
PP-300/255	300	255	480
PP-625/260	625	260	525
PP-1050/310	1050	310	560
PP-1150/345	1150	345	750
PP-1850/265	1850	265	725
PP-3350/420	3350	420	1220
PET-45/235	45	235	265
PET-150/70	150	70	80
PET-300/200	300	200	280
PET-500/315	500	315	375
PET-550/300	550	300	360
PET-625/175	625	175	200
PET-800/75	800	75	115
PET-900/180	900	180	205
PET-1400/185	1400	185	117
PET-1800/345	1800	345	470
PET-1850/330	1850	330	535
PET-2150/290	2150	290	420
PET-3200/300	3200	300	530
PET-3850/430	3850	430	740
E-CTFE-165/420	165	420	350
E-CTFE-260/430	260	430	370

Änderungen vorbehalten

Verfügbare Gewebebreiten auf Anfrage. Andere Gewebe auf Anfrage.